

Tech Sheet – Restoration Shop UB

DESCRIPTION



Restoration Shop UB – Urethane Basecoat

Restoration Shop **UB Basecoat** is a state-of-the-art, basecoat/clearcoat system designed to reproduce the hi-tech O.E.M. finishes found on today's vehicles. It features outstanding coverage, rapid dry time, excellent metallic control and optimum reparability.

COMPONENTS



- UB - High Performance Base Color
- UR 60 - Urethane Reducer Fast
- UR 70 - Urethane Reducer Medium
- UR 85 - Urethane Reducer Slow



POT LIFE @ 77°F



When properly covered at 77°F UB Basecoat will maintain a sprayable viscosity indefinitely

MIXING RATIO



Mixing Ratios: **2 : 1** 2 parts UB Color – 1 part UR Reducer.

CLEAN UP



KT912 (Check local regulations)

SUBSTRATES



UB Series Urethane Basecoat may be applied over: Cleaned, sanded and primed OEM or Refinish topcoat. Kustom Shop **KEP** Epoxy Primer / Sealer. Kustom Shop **KUP** Urethane Primer. Kustom Shop **KFP** Hi-Build 2K Primer Surfacer Kustom Shop **KPP** Polyester Primer, Kustom Shop **KL611** Old school Acrylic Lacquer Primer.

- Epoxy Primer
- Properly Prepared OEM Surface
- Properly Prepared Aluminum and Steel.

SURFACE PREPARATION



USE RECOMMENDED UNDERCOAT SYSTEM FOLLOWING RECOMMENDED PROCEDURES.

- Wipe with KW901 Grease and Wax Remover or KW902 Anti-Static Panel Kleaner
- Abrade with 150 grit then 320 grit sandpaper or equivalent.
- Wipe again with KW901 Grease and Wax Remover or KW902 Anti-Static Panel Kleaner
- For best results apply anti-corrosive primer such as KEP Series epoxy primers over bare metal.



APPLICATION



For Air Spray

- Spray 2 - 3 medium-wet coats with an overlap of 50% until full hiding is achieved
- Allow 5-10 minutes @ 70° F flash time between coats
- Dry mils 2.0 to 3.0 mils. Wet mils 4.0 to 6.5 mils.
- Surface temperature should be 50-100°F with less than 80% ambient humidity preferred.

Tech Sheet – Restoration Shop UB

FLASH / DRY TIMES



AIR DRY @ 77°F

Flash Between Coats.....	5-10 Minutes
To Tape.....	20-40 Minutes
To Clearcoat.....	30 Minutes

Note: If the basecoat is allowed to dry more than 24 hours, it must be scuffed and new basecoat applied.

Clear Coating: **KC210** Urethane Speed Clear with **KH212** Overall Hardener or **KC310** Super Flow Polyurethane Clear with **KH311** Hardener.

GUN SETUPS



CONVENTIONAL

Gravity Feed.....	1.3 mm - 1.5 mm
Siphon Feed.....	1.6 mm - 1.8 mm

HVLP

Anest Iwata LPH 400	1.2 mm - 1.4 mm tip
Binks MG1.....	1.3 mm - 1.5 mm tip
Devilbiss GTI	1.4 mm - 1.6 mm tip
Sata 95 & 2000	1.3 mm - 1.5 mm tip

AIR PRESSURES



CONVENTIONAL @ GUN

Gravity Feed	35 - 40 psi
Siphon Feed.....	45 - 50 psi

HVLP @ Cap 8 - 10 psi

PHYSICAL DATA (2:1) Base Color

VOC (Volatile Organic Content).....	5.69 lbs/gal (682 g/l)
VOC UR Reducers.....	7.52 lbs/gal (902 g/l)
VOC X70 Reducers.....	0.00 Exempt
Flash Point	27°F

SAFETY



Before using any Restoration Shop product, be sure to read all MSDS and application instructions and warnings. Always wear a properly fitted air purifying respirator with organic vapor cartridges and particulate filter or a fresh air respirator (depending on product selection), eye protection, gloves and protective clothing during application and until vapors are exhausted. Do not permit anyone without protection in the painting area. This product is intended for use by a professionally trained painter. **Keep out of the reach of children.**

IMPORTANT: The data on this sheet represent typical values obtained by the methods indicated. Since application variables are a major factor in product performance, this information should serve only as a general guide. Restoration Shop assumes no obligation or liability for use of this information. Unless Restoration Shop agrees otherwise in writing, RESTORATION SHOP MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. RESTORATION SHOP WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Unless Restoration Shop agrees otherwise in writing, Restoration Shop's only obligation for any defect in this product under any warranty that Restoration Shop provides or under any other legal theory will be to replace the defective product, or to refund its purchase price, at Restoration Shop's option.